

DUPONT™ TYVEK® FOR MEDICAL AND PHARMACEUTICAL PACKAGING SPECIFICATION PROPERTIES

Table I. Specification properties of DuPont™ Tyvek® (metric units)

Property	Comparable Test Method	Units	Tyvek® 1073B	Tyvek® Asuron™	Tyvek® 1059B	Tyvek® 2FS™
Basis Weight	ASTM D3776 ¹ EN ISO 536 ¹	(g/m ²)	74.6 [71.2–78.0]	67.5 [64.5–70.5]	64.4 [61.7–67.1]	59.5 [56.5–62.5]
Delamination	ASTM D2724 ²	(N/2.54 cm)	2.3 [1.6–3.1]	2.4 [2.0–2.9]	2.2 [1.5–2.9]	2.7 [2.1–3.3]
Gurley Hill Porosity	TAPPI T460 ¹ ISO 5636-5 ³	sec/100 cc	22 [8–36]	26 [16–40]	20 [8–36]	22 [9–35]

Notes: Specification properties are controlled to a nominal value and released within specifications. The customer is responsible for determining that Tyvek® is suitable for the intended application. The ranges represent the controlled minimum and maximum values in which the product is released. Specification properties are typical values based on roll averages, with samples taken uniformly across the sheet. These properties are representative for uncoated Tyvek® as sold by DuPont. Any downstream operations, such as coatings applied by sterile packaging manufacturers (SPMs), may change these values.

1. Modified sample size.
2. Modified for speed and gauge length.
3. Modified for sealing fluid characteristics.

Table II. Specification properties of DuPont™ Tyvek® (English units)

Property	Comparable Test Method	Units	Tyvek® 1073B	Tyvek® Asuron™	Tyvek® 1059B	Tyvek® 2FS™
Basis Weight	ASTM D3776 ¹ EN ISO 536 ¹	oz/yd ²	2.20 [2.10–2.30]	1.99 [1.90–2.08]	1.90 [1.82–1.98]	1.76 [1.67–1.84]
Delamination	ASTM D2724 ²	lbj/in.	0.5 [0.4–0.7]	0.5 [0.4–0.6]	0.5 [0.3–0.7]	0.6 [0.5–0.7]
Gurley Hill Porosity	TAPPI T460 ¹ ISO 5636-5 ³	sec/100 cc	22 [8–36]	26 [16–40]	20 [8–36]	22 [9–35]

Notes: Specification properties are controlled to a nominal value and released within specifications. The customer is responsible for determining that Tyvek® is suitable for the intended application. The ranges represent the controlled minimum and maximum values in which the product is released. Specification properties are typical values based on roll averages, with samples taken uniformly across the sheet. These properties are representative for uncoated Tyvek® as sold by DuPont. Any downstream operations, such as coatings applied by sterile packaging manufacturers (SPMs), may change these values.

1. Modified sample size.
2. Modified for speed and gauge length.
3. Modified for sealing fluid characteristics.

For more information about DuPont™ Tyvek® for medical and pharmaceutical packaging and to find out how we can help you with packaging and regulatory compliance, call us today at 1.800.44.TYVEK or visit us at www.MedicalPackaging.DuPont.com.



The miracles of science™

This information is based upon technical data that DuPont believes to be reliable. It is subject to revision as additional knowledge and experience are gained. DuPont makes no guarantee of results and assumes no obligation or liability in connection with this information. It is intended for use by persons having technical skill for evaluation under their specific end-use conditions at their own discretion and risk. Since conditions of use are outside our control, WE MAKE NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING WITHOUT LIMITATIONS, NO WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE AND ASSUME NO LIABILITY IN CONNECTION WITH ANY USE OF THIS INFORMATION.

This information is not intended as a license to operate under or a recommendation to infringe any patent or technical information of DuPont or others covering any material or its use.

Copyright © 2011 DuPont. All rights reserved. The DuPont Oval Logo, DuPont™, The miracles of science™, Tyvek®, Tyvek® Asuron™ and Tyvek® 2FS™ are trademarks or registered trademarks of E.I. du Pont de Nemours and Company or its affiliates. (11/11)